

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : D01D 5/08, D01F 6/06	A1	(11) International Publication Number: WO 00/53830
		(43) International Publication Date: 14 September 2000 (14.09.00)

(21) International Application Number: PCT/GB00/00814

(22) International Filing Date: 6 March 2000 (06.03.00)

(30) Priority Data:
9905145.0 6 March 1999 (06.03.99) GB(71) Applicant (for all designated States except US): BOLTON
INSTITUTE OF HIGHER EDUCATION [GB/GB]; Higher
Education Corporation, Deane Road, Bolton BL3 5AB (GB).

(72) Inventors; and


(75) Inventors/Applicants (for US only): ALDERSON, Kim, Lesley
[GB/GB]; 21 Kent Road, Formby, Liverpool L37 6BG (GB).
SIMKINS, Virginia, Ruth [GB/GB]; Tonaclyffe House,
Tonaclyffe Road, Whitworth, Nr. Rochdale, Lancashire
OL12 8SS (GB).(74) Agents: QUEST, Barry et al.; Wilson Gunn M'Caw, 41-51
Royal Exchange, Cross Street, Manchester M2 7BD (GB).(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG,
BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE,
ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP,
KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA,
MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU,
SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG,
US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE,
LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM,
AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT,
BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU,
MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published

With international search report.

Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.

(54) Title: AUXETIC MATERIALS



(57) Abstract

An auxetic material, which has a negative Poisson ratio so that it has the property of expanding or contracting transversely to a direction in which it is extended or compressed, is made in filamentary or fibrous form. A suitable process involves cohering and extruding heated polymer powder so that the cohesion and extrusion is effected with spinning to produce auxetic filaments. Typically the powder is heated to a temperature sufficient to allow some degree of surface melting yet not high enough to enable bulk melting.